

MAGNEBOND[®] UL-180

Properties

Magnebond[®] UL-180 has the following characteristics:

- thermal index of 160°C,
- solderable at 390°C without previous removal of the enamel coating,
- very good thermal properties,
- excellent winding properties,
- high resoftening temperature,
- bondable under the action of heat resulting in a bonded coil with similar properties to trickle resin or impregnated coils.

Insulation

Magnebond[®] UL-180 is a solderable polyurethane enameled copper wire. The final layer is a polyamide aliphatic bondcoat.

Application

Magnebond[®] UL-180 is designed for the production of self-bonded windings, produced without supporting bobbins and without impregnation, but by either moulding or pressure. It is recommended for windings which need a good compromise between solderability and bonding.

Bonding the coil is rapidly achieved in the production line resulting in higher productivity.

Applications:

- deflection yokes for monitors,
- electrical motors,
- solenoids.

Production range

The standards are:

Diameter:	0.15 to 1.00 mm
Thickness:	Grade 1B and Grade 2B
Color:	Natural

Characteristics

Magnebond[®] UL-180 fulfills the requirements of the following specifications:

IEC 60317-35
NEMA MW 3C

Using conditions

The key conditions to be respected are the following :

- bonding temperature between 170 and 200°C, according to the type of aliphatic polyamide bondcoat used (information on request from our technical department)
- accurate quantity of energy applied during bonding process, bonding the coils can be achieved by the joule-effect heating technique.

The values for the intensity and voltage to be applied to the ends of a coil, can be determined as follows :

$$70 M = RI_2t$$

M = mass of wire in grams
R = resistance in Ohms
I = intensity in Amperes
t = length of time in seconds

MAGNEBOND® UL-180

MAGNEBOND® UL-180

Valeurs typiques d'un fil Magnebond® UL-180 mesurées selon les normes CEI 60 851	Typical values for a Magnebond® UL-180 sample according to IEC 60 851 standards	
Diamètre du conducteur Diamètre sur émail Isolation de base Isolation thermo-adhérente	0,50 0,561 Polyuréthane Polyamide aliphatic	Conductor Diameter Overall Diameter Basecoat Bondcoat
Principales caractéristiques		Main characteristics
Indice de température	160°C	Thermal index
Durée de vie de 5000 h à	180°C	5000 h life test
Choc thermique	OK at 200°C	Heat shock
Thermoplasticité	≥ 250°C	Cut through temperature
Tension de claquage	≥ 1,5 x IEC values	Breakdown voltage
Soudabilité	390°C, 4 sec.	Soderability
Flexibilité	10 % + 1 diam.	Flexibility
Allongement	40 %	Elongation
Tangente Delta (isolation de base)	≥ 165°C	Tangente Delta (basecoat)
Température de ramolissement (Méthode CEI 60 851-3/7-1 sur bobinage hélicoïdal)	≥ 160°C	Resoftening Temperature (According to helical coil test IEC 60-851-3/7-1)

Valeurs typiques d'un fil Magnebond® UL-180 mesurées selon les normes CEI 60 851	Typical values for a Magnebond® UL-180 sample according to IEC 60 851 standards	
Diamètre du conducteur Diamètre sur émail Isolation de base Isolation thermo-adhérente	0,90 0,984 Polyuréthane Polyamide aliphatic	Conductor Diameter Overall Diameter Basecoat Bondcoat
Principales caractéristiques		Main characteristics
Indice de température (isolation de base)	190°C	Thermal index (basecoat)
Durée de vie de 5000 h à (isolation de base)	200°C	5000 h life test (basecoat)
Choc thermique	200°C	Heat shock
Thermoplasticité	≥ 250°C	Cut through temperature
Tension de claquage	≥ 1,5 x IEC values	Breakdown voltage
Soudabilité	390°C, 5 sec.	Soderability
Flexibilité	10 % + 1 diam.	Flexibility
Allongement	42 %	Elongation
Tangente Delta (isolation de base)	≥ 165°C	Tangente Delta (basecoat)
Température de ramolissement (Méthode CEI 60 851-3/7-1 sur bobinage hélicoïdal)	≥ 160°C	Resoftening Temperature (According to helical coil test IEC 60-851-3/7-1)

These values are for information only.

